

## MIL-DTL 24643/65 Multi-179 Coax Cable

## 3C RG179 and 6C RG179, Non Water-Blocked


**Champlain Cable** has a long history of success in the development and manufacture of data communication cables. We are the <u>first</u> supplier to be qualified by the US Naval Sea Systems Command (NAVSEA) for supply of all variants of MIL-DTL 24643/65. With over 10 years of various first-QPL approvals totaling <u>over 25 million</u> feet of data cables installed on Naval vessels, no one else comes close. **Dataclear**<sup>®</sup> is the brand you can count on for Reliability, Service and Price.

**Dataclear**<sup>®</sup> **Marine/65** cables are Low Smoke Zero Halogen (LSZH) coaxial data cables to serve the shipboard market. **Dataclear**<sup>®</sup> **Marine/65** provides two major solutions for shipboard communications:

• Replacement of halogenated insulations (PVC, Fluoropolymer) in confined shipboard compartments, thereby eliminating a major source of halogenated toxic gases in the event of fire.

• Maintains exceptional voice and data transmission communication capabilities in accordance with or exceeding commercial Coaxial protocol standards.

MIL-DTL 24643/65 Type	Number of Coaxes	Conductor	Shield per Line	Water- blocked	Jacket Color	Cable OD (nom)
LS3C179DT-01U0	3	28 solid TC	Double	No	Black	0.350"
LS6C179DT-02U0	6	28 solid TC	Double	No	Black	0.440"







## MIL-DTL 24643/65 Multi-179 Coax Cable

ELECTRICAL PROPERTIES				
DC Resistance, max.	110 Ohms/1000 ft			
DC Resistance Unbalance, max	5%			
Char. Impedance (0.2 to 20 MHz)	75 Ohms +/-5 Ohms			
Voltage Withstand—Cond to Cond	2.0KVAC			
Voltage Withstand—Cond to Shield[s]	1.0KVAC			

PHYSICAL PROPERTIES				
Tensile Strength:				
Insulation (Un-aged)	600 min			
Jacket (Un-aged)	1300 min			
Insulation (Retention after 168hrs at 136°C)	95% min			
Jacket (Retention after 168hrs at 136°C)	90% min			
Elongation:				
Insulation (Un-aged)	160% min			
Jacket (Un-aged)	160% min			
Insulation (Retention after 168hrs at 136°C)	90% min			
Jacket (Retention after 168hrs at 136°C)	80% min			
Cross-link proof test (Jacket, Percent maximum)	50%			
Flame Propagation (Cable)*	No Failure			

We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss and damage arising from the handling and use of our products whether used alone or in combination with other products.



Manufacturing Locations Colchester, Vermont El Paso, Texas